



## TECHNICAL DATA SHEET

### **Anti-moisture insulation foil a STROTEX HOTFLOOR**

#### **1. Intended use:**

For use in installations of underfloor heating systems (for and behind heating elements), for protecting expanded polystyrene boards against moisture from the mortar, in renovation works carried out in order to increase the energy efficiency of buildings under screed on a standard floor, as effective insulation against steam and moisture. It is recommended to lay the Strotex Hotfloor films with the print upwards and put the layers together with an overlap, additionally glued with aluminum tape.

#### **Declared technical parameters:**

| <b>Product index</b>                        |                                    | <b>FH1000*0100*50, FH1000*0130*50</b>                 |                            |                  |                    |
|---|------------------------------------|---|----------------------------|------------------|--------------------|
| <b>Plastic type</b>                         |                                    | PE-LD, PP, metallized polypropylene film              |                            |                  |                    |
| <b>Intended use</b>                         |                                    | Anti-moisture insulation foil, for underfloor heating |                            |                  |                    |
| <b>Recommended application temperatures</b> |                                    | +5°C ÷ +55°C  |                            |                  |                    |
| <b>Parameters</b>                           |                                    | <b>Declared value</b>                                 |                            | <b>Units</b>     | <b>Test method</b> |
|   |                                    | <b>FH1000*0100*<br/>50</b>                            | <b>FH1000*0130*<br/>50</b> |                  |                    |
| <b>Dimensions</b>                           | Thickness                          | 0,100 ± 20%   | 0,130 ± 20%                | mm               | EN 1849-2          |
|   | Weight                             | 93 ± 20%  | 120 ± 20%                  | g/m <sup>2</sup> |                    |
|   | Roll lenght                        | 50 ± 2%   |                            | m                | PN-EN 1848-2       |
|   | Width                              | 1,0 ± 3%  |                            | m                |                    |
|   | Overlap's width                    | 3 - 4   |                            | cm               | --                 |
| <b>Breaking strength</b>                    | Along                              | > 25  |                            | MPa              | EN 527-3           |
|   | Across                             | > 40  |                            | MPa              |                    |
| <b>Elongation at break</b>                  | Along                              | > 50  |                            | %                |                    |
|   | Across                             | > 10  |                            | %                |                    |
| <b>Watertightness at 2 kPa</b>              |                                    | Pass  |                            | --               | EN 1928            |
| <b>Impact resistance</b>                    |                                    | ≤150  | ≤150                       | mm               | EN 12691           |
| <b>Resistance</b>                           | Waterproof after artificial ageing | Pass  |                            | --               | EN 1296            |
|   | Alkali                             |   |                            |                  | EN 1928            |
| <b>Low temperature resistance</b>           |                                    | -30   |                            | °C               | EN 1847            |
| <b>Reaction to fire</b>                     |                                    | F   |                            | Klasa            | EN 1928            |
| <b>Hazardous substances</b>                 |                                    | NPD   |                            | --               | --                 |